

**CASCO RESIN WW-3125M/S**

Casco Resin WW-3125M/S , a E2 grade UF particleboard resin with excellent application properties.

Appearance	Milky white liquid, free from lumps and visible impurities
Viscosity @ 30°C (2/60)	120 - 220 cPs
pH @ 30°C	7.8 – 8.5
Specific Gravity @ 30°C	1.280 – 1.295
Solid Content @ 105°C, 3 hrs.	64 – 66%
BWG @ 100°C	42 – 58 seconds
Free Formaldehyde (After 17 hours)	0.10 – 0.30 %
Storage life @ 32°C / Ambient temperature	2 weeks from manufacturing date

**Glue mix for checking BWG**

Resin	100g
Water	2ml
Ammonium Chloride	0.5 g

**Application: Particle board**

Asta Chemicals Sdn. Bhd. (15459-U)  
(Formerly known as Momenive Specialty Chemicals Sdn. Bhd.)  
Unit A-28-12, Level 28  
Menara UOA Bangsar  
No: 5 Jalan Bangsar Utama 1  
59000 Kuala Lumpur, Malaysia.  
+60 3 2284 9118  
+60 3 2283 1807 (fax)

For worldwide locations visit  
[www.astachemicals.com](http://www.astachemicals.com)

ASTA CHEMICALS MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING ANY PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY ASTA CHEMICALS, EXCEPT THAT THE PRODUCT SHALL CONFORM TO CONTRACTED SPECIFICATIONS, AND THAT THE PRODUCT DOES NOT INFRINGE ANY VALID UNITED STATES PATENT. THE INFORMATION PROVIDED HEREIN BELIEVED BY ASTA CHEMICALS TO BE ACCURATE AT THE TIME OF PREPARATION OR PREPARED FROM SOURCES BELIEVED TO BE RELIABLE, BUT IT IS THE RESPONSIBILITY OF THE USER TO INVESTIGATE AND UNDERSTAND OTHER PERTINENT SOURCES OF INFORMATION, TO COMPLY WITH ALL LAWS AND PROCEDURES APPLICABLE TO THE SAFE HANDLING AND USE OF THE PRODUCT AND TO DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE.