

CASCO RESIN WW3130E/A/S

| Product Physical Properties: (at time of manufacturing) | |
|---|--|
| Appearance | Clear to off-white solution and free from suspended impurities |
| Viscosity @ 30°C (2/60), cps | 200 - 270 |
| pH @ 30°C | 7.7 – 8.2 |
| Specific Gravity @ 30°C | 1.274 – 1.292 |
| Solid Content, % (105°C @ 3 hours, Neat) | 64 – 66 |
| BWG @ 100°C, sec (125g resin + 5ml 25% NH ₄ Cl + 10ml H ₂ O) | 40 – 55 |
| Free Formaldehyde, % (After 17 hours) | 0.25 - 0.45 |
| Water Tolerance 30°C, % w/w | > 100% |
| Storage life @ 32°C/ Ambient temperature | 2 weeks from Manufacturing Date |

Asta Chemicals Sdn. Bhd. (15459-U)
(Formerly known as Momentive Specialty Chemicals Sdn. Bhd.)
Unit A-28-12, Level 28
Menara UOA Bangsar
No: 5 Jalan Bangsar Utama 1
59000 Kuala Lumpur, Malaysia.
+60 3 2284 9118
+60 3 2283 1807 (fax)

For worldwide locations visit
www.astachemicals.com

ASTA CHEMICALS MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING ANY PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY ASTA CHEMICALS, EXCEPT THAT THE PRODUCT SHALL CONFORM TO CONTRACTED SPECIFICATIONS, AND THAT THE PRODUCT DOES NOT INFRINGE ANY VALID UNITED STATES PATENT. THE INFORMATION PROVIDED HEREIN BELIEVED BY ASTA CHEMICALS TO BE ACCURATE AT THE TIME OF PREPARATION OR PREPARED FROM SOURCES BELIEVED TO BE RELIABLE, BUT IT IS THE RESPONSIBILITY OF THE USER TO INVESTIGATE AND UNDERSTAND OTHER PERTINENT SOURCES OF INFORMATION, TO COMPLY WITH ALL LAWS AND PROCEDURES APPLICABLE TO THE SAFE HANDLING AND USE OF THE PRODUCT AND TO DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE.